

Test Report

No. CANHG2202363901

Date: 28 Feb 2022

Page 1 of 3

Client Name : MAYMOM LLC

Client Address : NO. 20-7, ALY 19, LN 333, CHUNGCHENG RD. CHUNAN, MIAOLI COUNTY, TAIWAN

Sample Name : screw ring for wide mouth bottle

Client Ref. Info. : The batch No. of PP216-Th71.b is R20220112-16 The batch No. of PP116-Th61.b is R20220127-3. The batch No. of PP116-wC.b is R20220127-1.

Material : PP

Buyer : AMAZON AND OTHERS

Manufacturer : MAYMOM

The above sample(s) and information were provided by the client.

SGS Job No. : XMHL2202000770CW (XMIN2202001286SC) - XM

Date of Sample Received : 21 Feb 2022

Testing Period : 21 Feb 2022 - 28 Feb 2022

Test Requested : Selected test(s) as requested by client.

Test Method : Please refer to next page(s).

Test Results : Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004,(EU) No 10/2011 and its amendment (EU) 2020/1245 Regulation- Overall migration	PASS

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch

Kim Cai

Kim Cai
Approved Signatory

scan to see the report



CANHG2202363901



SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch Testing Center Chemical Laboratory.

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

198 Kazhu Road, Sciencetech Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663

中国·广州·经济技术开发区科学城科珠路198号 邮编: 510663

t (86-20) 82155555 www.sgs.com

t (86-20) 82155555 sgs.china@sgs.com

Test Results :

Test Part Description :

Specimen No.	SGS Sample ID	Description	Material (claimed by the client)
SN1	CAN22-023639.001	Lt-blue plastic lid	PP

Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004, (EU) No 10/2011 and its amendment (EU) 2020/1245 Regulation– Overall migration

Test Method : With reference to Commission Regulation (EU) No 10/2011 of 14 January 2011 Annex III and Annex V for selection of condition and EN 1186-1:2002 for selection of test methods; or EN 1186-3:2002 aqueous food simulants by total immersion method;

Sample 001

Simulant Used : 50% Ethanol (V/V) Aqueous Solution
 Test Condition : 70 °C 2.0 hr(s)

<u>Test Item(s)</u>	<u>Max. Permissible Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>Test result</u>
Area/Volume	-	dm ² /kg	-	5.7
First Migration	-	mg/kg	20	<20
Second Migration	-	mg/kg	20	<20
Third Migration	60	mg/kg	20	<20
Stability				YES
Comment				PASS

Notes :

1. mg/dm² = milligram per square decimeter
mg/kg = milligram per kilogram of foodstuff in contact with
2. °C = degree Celsius
3. Analytical tolerance of aqueous simulants is 2mg/dm² or 12mg/kg
4. Analytical tolerance of fatty food simulants is 3mg/dm² or 20mg/kg



Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***

